Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2021-01-06-18** **Date: 03/12/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-11-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	26/11/2020	03/12/2020	150.42 X 150.54 X 150.45	22644	8.312	389.5	17.2	17.2
2	PCC	M15	26/11/2020	03/12/2020	150.42 X 150.54 X 150.45	22644	8.331	398.5	17.6	
3	PCC	M15	26/11/2020	03/12/2020	150.32 X 150.54 X 150.35	22629	8.345	380.2	16.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

CIVIL PRO
AN ISO 9001 : 2008 COMPANY &NABL ACCREDITED LABORATORY AS PER ISO/IEC 17025:2005
4, 7TH MAIN MALLESWARAM, BANGALORE -3
Certificate No.: TC-5548

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2021-01-06-18** **Date: 24/12/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-11-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	26/11/2020	24/12/2020	150.42 X 150.54 X 150.45	22644	8.312	538.9	23.8	23.5
2	PCC	M15	26/11/2020	24/12/2020	150.42 X 150.54 X 150.45	22644	8.331	518.6	22.9	
3	PCC	M15	26/11/2020	24/12/2020	150.32 X 150.54 X 150.35	22629	8.345	536.3	23.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CEMENT CONCRETE FLOORING TILES

Lab ID	:	**CP-2021-01-06-18** **Date: 19-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	*14-12-20*
Sample Type	:	*Pre-Polished Designer Cement Concrete Tiles*
Reference to BIS codes	:	IS 1237:2012
Date of test	:	14-12-20

1. Water Absorption

Sl.No.	Measured Dimension (mm)			Water Absorption	Average	Requirement as per IS:1237-2012
	L	B	T	(%)	(%)	
1	400	399	25.09	2.530	2.21	The average percentage of water absorption shall not exceed 10.
2	401	401	25.05	1.920		
3	400	401	25.11	2.170		
4	400	399	25.06	2.060		
5	399	400	25.17	1.800		
6	400	400	25.13	2.760		

2.Wet Transverse Strength

Sl.No.	Measured Dimension (mm)			Wet Transverse Strength	Average	Requirement as per IS:1237-2012
	L	B	T	(N/mm^2)	(N/mm^2)	
1	401	401	25.02	7.83	7.8	The average wet transverse strength shall not be less than $3N/mm^2$.
2	401	401	25.04	8.16		
3	400	399	25.06	7.51		
4	399	401	25.01	7.88		
5	400	400	25.05	8.25		
6	401	399	25.03	7.29		

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date. BANGALORE

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL | GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

CEMENT CONCRETE PRECAST CONCRETE BLOCKS FOR PAVING

Lab ID	:	**CP-2021-01-06-18** **Date: 09-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	04-12-20
Sample Type/ Size	:	Precast concrete blocks for paving
Reference to BIS codes	:	IS 15658:2006
Date of test	:	04-12-20

1.Compressive Strength

Sl.No.	Dimension (mm)			Compressive Strength	Average
	L	B	T	(N/mm^2)	(N/mm^2)
1	197.22	159.88	75.99	32.5	33.1
2	198.48	159.64	75.25	33.8	
3	199.54	159.54	75.48	32.5	
4	197.68	159.22	75.55	33.5	
5	198.11	159.87	75.32	32.8	
6	198.18	160.02	75.11	33.4	
7	198.45	158.99	75.98	33.2	
8	197.22	159.22	75.12	32.8	

2. Water Absorption

Sl.No.	Wet Weight	Dry weight	Thickness	Water Absorption (%)	Average (%)
1	4.987	4.828	75.85	3.29	3.64
2	4.898	4.721	75.22	3.75	
3	4.988	4.802	75.44	3.87	

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

CIVIL Pro Sig. Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

End of Report

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL |
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES |

TEST RESULTES FOR MS BLOCK PIPE

Lab ID	:	**CP-2021-01-06-18** **Date: 14-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Agency	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Project Name	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	11-12-20
Type of Sample	:	M.S Block Pipe
Reference to BIS codes	:	IS:1608-2005(RA 2011), IS 1599-2012.
Date of test	:	11-12-20

TESTS RESULTS FOR MS BLOCK PIPE 38MM DIA, 14 GAUGE

Sl. No	Description	Result	Required as per as IS Code 2062: 2011	Remarks
1	Yeild Stress (N/mm2)	299	250N/mm^2	Satisfactory
2	Tensile Strength (N/mm2)	509	410N/mm^2	Satisfactory
3	Elongation Percentage (%)	24	Min 23%	Satisfactory

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

TEST RESULTES FOR MS RECTANGULAR POLE

Lab ID : **CP-2021-01-06-18** **Date: 09-12-20**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Sourse of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 07-12-20

Type of Sample : M.S Rectangular Pole(65X65X6)mm

Reference to BIS codes : IS:1608-2005(RA 2011), IS 1599-2012.

Date of test : 07-12-20

TESTS RESULTS FOR M.S RECTANGULAR POLES MADE OUT OF 2 EQUAL ANGLES OF 65 X 65 X 6 MM WELDED TOGETHER

SL.NO	Description	Result	Required as per IS Code 2062:2011	Remarks
1	Weight/Meter (Kg /m)	5.81	5.8 Kg/m	Satisfactory
2	Yeild stress (N/mm2)	278	250N/mm^2	Satisfactory
3	Tensile Strength (N/mm2)	485	410N/mm^2	Satisfactory
4	Elongation Percentage (%)	23.5	Min23%	Satisfactory
5	Bend Test	Satisfactory	Should not Crack or fracture	Satisfactory

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date. BANGALORE

FOR CIVIL Pro
R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST RESULTS FOR CHAIN LINK FENCING

Lab ID	:	**CP-2021-01-06-18** **Date: 11-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Sourse of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	09-12-20
Type of Sample	:	Chain Link Fencing
Reference to BIS codes	:	IS 2062:2011
Date of test	:	09-12-20

TESTS RESULT FOR WIRE MESH		
SL.NO	**Description**	**Result**
1	**Average Thickness in mm**	4.04
2	**Dia of linewire in mm**	3.14
3	**Mesh size in mm**	50.01
4	**Nominaldia of meshwire in mm**	2.52
5	**Bend Test**	Satisfactory

* The results obtained are satisfactory as per standard requirements.

Note:
The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

****End of Report****

TEST RESULTS OF GRADATION FOR WMM

Lab ID : **CP-2021-01-06-18** **Date: 24-11-20**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 21-11-20

Type of Mix : WMM (Wet Mix Macadam)

Date of Test : 21-11-20

Oven Dry Weight : 11000 Grams

IS Sieve Size(mm)	Weight Retained (gm)	Cumulative Weight Retained (gm)	% Cumulative Weight Retained	% Passing	Spec.I.Vide Table 400.13 MORTH Specification
53	0	0	0.0	100.0	100
45	315	315	2.9	97.1	95-100
22.4	2259	2574	23.4	76.6	60-80
11.2	2179	4753	43.2	56.8	40-60
4.75	2251	7004	63.7	36.3	25-40
2.36	1621	8625	78.4	21.6	15-30
0.6	623	9248	84.1	15.9	8-22
0.075	1338	10586	96.2	3.8	0-5

* The results obtained are satisfactory as per standard requirements.

Note:-

The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL PRO Sign Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

TEST REPORT OF AGGEGRATE IMPACT VALUE
IS: 2386 Part IV

Lab ID	:	**CP-2021-01-06-18** **Date: 24-11-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-11-20
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of Test	:	21-11-20

Sl.No	Particulars of observations	Index	TEST 1	TEST 2
1	Total weight of the surface dry sample sample (passing 12.5 mm and retained on 10mm sieve)	A	300.2	300.2
2	Weight of fraction passing 2.36mm sieve After giving 15 blows	B	73.9	74.0
3	weight of fraction retained 2.36mm sieve After giving 15 blows	C	225.9	225.8
4	Total weight of (B+C) is less than the initial weight (Weight A) by more than one gram the result shall be discarded and a fresh test made.	A-(B+C)	0.4	0.4
5	Aggregate impact value	(B/A)*100	24.6	24.7
6	Aggregate impact value (Mean of two tests)	Pecentage	24.6	

* The results obtained are satisfactory as per standard requirements.

Note:-

The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sign Date BANGALORE

FOR CIVIL Pro.
R RUDRAPRASAD
Authorized Signatory
Technical Manager

End of Report

DETERMINATION OF FLAKINESS INDEX AND ELONGATION INDEX OF COARSE AGGREGATE(IS 2386 (Part 1) 1963 (RA 2007)

Lab ID	:	**CP-2021-01-06-18** **Date: 24-11-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	21-11-20
Type of Mix	:	Coarse Aggregate for WMM (Wet Mix Macadam)
Date of Test	:	21-11-20

Result:

Index	Percentage of Flakiness and Elongation Index	Secified limits as per MORTH specification table 400-12
Flakiness Index	12.8%	Combined Flakiness & Elongation Index for WMM is Maximum 35%
Elongation Index	12.5%	
Combined Flakiness and Elongation Index for WMM	25.3%	

* The results obtained are satisfactory as per standard requirements.

Note:-

The results pertain to the samples received and tested.
All information Furnished by Customer/ Representative
Any correction in the report will make this report invalid.
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig Date BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

End of Report

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2021-01-06-18** **Date: 20-11-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample condition	:	Satisfactory
Date of Receipt	:	17-11-20
Sample Type	:	40mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	17-11-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 40MM DOWN COARSE AGGREGATE:

Total weight taken : 15000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	80 mm	0	0	0.0	100	100
2	40 mm	215	215	1.4	98.6	90-100
3	20 mm	7455	7670	51.1	48.9	30-70
4	10 mm	4266	11936	79.6	20.4	10-35
5	4.75 mm	2844	14780	98.5	1.5	0-5
6	Pan	220	15000	100.0	0	---

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL PRO BANGALORE Sig..... Date.....

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2021-01-06-18** **Date: 20-11-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	11.9	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	12.3	
3	Specific Gravity	2.64	–
4	Bulk Density(Loose) (Kg/l)	1.41	–
5	Bulk Density(Compacted) (Kg/l)	1.47	–
6	Water Absorption(%)	0.23	–

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig..... Date..... BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID	:	**CP-2021-01-06-18** **Date: 19-11-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-11-20
Sample Type/ Size	:	20mm down size coarse aggregate
Reference to BIS codes	:	IS: 383:2016 (Specification for Coarse and fine Aggregates) IS: 2386 :1963(Part - 1,3,4) RA2011 IS 2386 Part 1: Particle Size and Shape IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption IS 2386 Part 4: Mechanical Properties
Date of test	:	17-11-20

SIEVE ANALYSIS (PARTICLE SIZE DISTRIBUTION) OF 20MM DOWN COARSE AGGREGATE:

Total weight taken : 5000 grams

Sample No.	Sieve No.	Weight Retained in gms	Cumulative Weight Retained in gms	% Cumulative Weight Retained	% Passing	Required as per IS 383:2016
1	40 mm	0	0	0	100	100
2	20 mm	225	225	4.5	95.5	90-100
3	10 mm	2845	3070	61.4	38.6	25-55
4	4.75 mm	1745	4815	96.3	3.7	0-10
5	Pan	185	5000	100	0	–

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

Format No: CP/TF/01

TEST REPORT ON COARSE AGGREGATES

Lab ID : **CP-2021-01-06-18** **Date: 19-11-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS:383-2016
1	Flakiness Index(%)	13.2	Combined Flakiness & Elongation Index Shall not Exceed 40% for Uncrushed & Crushed Aggregate
2	Elongation Index(%)	10.1	
3	Specific Gravity	2.68	–
4	Bulk Density(Loose) (Kg/l)	1.43	–
5	Bulk Density(Compacted) (Kg/l)	1.49	–
6	Water Absorption(%)	0.23	–
7	Aggregate crushing Value(%)	22.9	Max 30% for Aggregates to be used in concrete for wearing Surface, In case Aggregate Crushing Value Exceeds 30% then the test for ten percent fines should be conducted for Aggregates to be used in concrete other than for wearing Surface.
8	Aggregate Impact Value(%)	23.7	30% for Aggregates to be used in concrete for wearing Surface, 45% for Aggregates to be used in concrete other than for wearing Surface.

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig. Date BANGALORE

Page 2/2
End of Report

Format No: CP/TF/01

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2021-01-06-18** **Date: 19-11-20**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 17-11-20

Sample Type : Fine Aggregate

Reference to BIS codes : IS 383 : 2016 (Specification for Coarse and fine Aggregates)
IS: 2386 :1963(Part - 1, 3) RA2012
IS 2386 Part 1: Particle Size and Shape
IS 2386 Part 3: Specific gravity, Density, Voids,Water Absorption

Date of test : 17-11-20

Total weight taken : 1000 grams

Sl.no	Sieve Size	Weight Retained (gms)	Cumulative Weight Retained (gms)	% Cumulative Weight Retained	% Passing	Requirement as per IS 383:2016			
						Grading Zone I	Grading Zone II	Grading Zone III	Grading Zone IV
1	10 mm	0	0	0.0	100.0	100	100	100	100
2	4.75 mm	27	27	2.7	97.3	90-100	90-100	90-100	95-100
3	2.36 mm	55	82	8.2	91.8	60-95	75-100	85-100	95-100
4	1.18 mm	239	321	32.1	67.9	30-70	55-90	75-100	90-100
5	600 micron	205	526	52.6	47.4	15-34	35-59	60-79	80-100
6	300 micron	203	729	72.9	27.1	5-20	8-30	12-40	15-50
7	150 micron	191	920	92.0	8.0	0-10	0-10	0-10	0-15
8	Pan	80	1000	100.0	0.0	---	---	---	---

Result :The tested Sample Conforms to Grading Zone II

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro BANGALORE Sig. Date

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

TEST REPORT OF FINE AGGREGATE

Lab ID : **CP-2021-01-06-18** **Date: 19-11-20**

PHYSICAL PROPERTIES

Sl.no	Tests	Result	Requirements as per IS 383:2016
1	Water Absorption(%)	1.5	–
2	Specific Gravity	2.59	–
3	Material finer than 75 micron(%)	6.9	Uncrushed fine Aggregate Max 3%, Crushed Fine aggregate Max 15%, Mixed Fine aggregate Max 12%, Manufactured Fine aggregate Max 10%

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

CIVIL Pro Sig. Date. BANGALORE

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

Format No: CP/TF/01

TEST REPORT OF PRECAST COVER SLAB

Lab ID : **CP-2021-01-06-18** **Date: 04-12-20**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 30-11-20

Sample Type /Size : Precast Cover Slab (100mm)

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete

Date of test : 30/11/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	(kg)	(Sq.mm)	(KN)	(N/mm^2)	(N/mm^2)	(N/mm^2)
1	Cover Slab-1	75.51	100.48	1.116	4477	80.9	18.1	16.8	21.0
2	Cover Slab-2	75.49	100.52	1.122	4475	82.3	18.4	17.1	21.4
3	Cover Slab-3	75.50	100.51	1.118	4476	81.5	18.2	16.9	21.2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE KERB STONE

Lab ID	:	**CP-2021-01-06-18** **Date: 07-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	02-12-20
Sample Type /Size	:	CC Kerb Stone/ 450*165*400mm
Reference to BIS codes	:	IS: 516 - 1959 Methods of Tests for Strength of Concrete
Date of test	:	02/12/2020

Sl. No.	Identification Mark	Diameter of the core	Height of the core	Weight of the core	Area	Failure Load	Core Compressive strength	Corrected Cylinder Compressive strength	Equivalent Cube Compressive strength
		(mm)	(mm)	Kg	(Sq.mm)	(KN)	(N/mm2)	(N/mm2)	(N/mm2)
1	A	100.01	165.51	2.864	7854	142.1	18.1	18.1	22.6
2	B	100.03	165.49	2.793	7857	145.2	18.5	18.5	23.1
3	C	100.01	165.50	2.815	7854	145.1	18.5	18.5	23.1

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL PRO Sig. Date BANGALORE

****End of Report****

M : 9972924526 | Tel : +91 80 23444801 | e : rechan6630@yahoo.co.in, civilproexperts@gmail.com

HIGHWAY & BUILDING MATERIALS TESTING LABORATORY | STRUCTURAL
GEO TECHNICAL | PROJECT MANAGEMENT | SURVEYING SERVICES

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2021-01-06-18** **Date: 03/12/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-11-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 7 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 03/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	26/11/2020	03/12/2020	150.42 X 150.54 X 150.45	22644	8.312	389.5	17.2	17.2
2	PCC	M15	26/11/2020	03/12/2020	150.42 X 150.54 X 150.45	22644	8.331	398.5	17.6	
3	PCC	M15	26/11/2020	03/12/2020	150.32 X 150.54 X 150.35	22629	8.345	380.2	16.8	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig..... Date..... BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF CEMENT CONCRETE CUBES

Lab ID : **CP-2021-01-06-18** **Date: 24/12/2020**

Customer : Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.

Address : Project Sub Division, BBMP, Bangalore.

Project Name : "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

Agency : Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.

Customer's Reference : EE(Project)/Ynk Zone/WO/118/2020-21

Source of Sample : Sample supplied by Agency

Sample Condition : Satisfactory

Date of Receipt : 28-11-20

Customer ID : PCC

Sample Type /Size : 150X150X150 mm

Sample grade/Age : M15 / 28 Days Compressive Strength

Reference to BIS codes : IS: 516 - 1959 Methods of Tests for Strength of Concrete Cl.5

Date of test : 24/12/2020

Sl. No.	Identification Mark	Grade of concrete	Date of Casting	Date of Testing	Dimension of the Specimen (mm)	Cross sectional area (Sq.mm)	Weight of the sample (kg)	Failure Load (KN)	Compressive strength (N/mm^2)	Average Compressive Strength (N/mm^2)
1	PCC	M15	26/11/2020	24/12/2020	150.42 X 150.54 X 150.45	22644	8.312	538.9	23.8	23.5
2	PCC	M15	26/11/2020	24/12/2020	150.42 X 150.54 X 150.45	22644	8.331	518.6	22.9	
3	PCC	M15	26/11/2020	24/12/2020	150.32 X 150.54 X 150.35	22629	8.345	536.3	23.7	

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL Pro Sig / Date BANGALORE

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

QC ABSTRACT

NAME OF WORK: "Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."

SL NO	Item Of Work	Name of Test	Frequency of Test/Quantity	Executed Quantity	Number of Tests Required	Number of Tests Conducted
		Materials				
1	Cement	Fineness by dry sieving	One Test		1	1
		Finess by Air permeablity method	One Test		1	1
		Density	One Test		1	1
		Standard Consistency	One Test		1	1
		Initial Setting time	One Test		1	1
		Final Setting time	One Test		1	1
		Soundness (Le Chatelier's Method)	One Test		1	1
		Compressive Strength	One Test		1	1
2	Coarse aggregate(40 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
3	Coarse aggregate(20 mm down size)	SIEVE ANALYSIS	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1
		Specific Gravity	One Test		1	1
		Bulk Density(Loose)	One Test		1	1
		Bulk Density(Compacted)	One Test		1	1
		Water Absorption	One Test		1	1
		Aggregate crushing Value	One Test		1	1
		Aggregate Impact Value	One Test		1	1
4	Fine aggregate	SIEVE ANALYSIS	One Test		1	1
		Water Absorption	One Test		1	1
		Specific Gravity	One Test		1	1
		Material finer than 75 micron	One Test		1	1
5	KERB	Core Compressive strength	One Test		1	1
		Corrected Cylinder Compressive strength	One Test		1	1
		Equivalent Cube Compressive strength	One Test		1	1
6	*Precast (100mm)*	Core Compressive Strength	One Test		1	1
		Corrected Cylinder Compressive *Strength*	One Test		1	1
		Equivalent Cube Compressive Strength	One Test		1	1
7	PCC(M15)	Compressive Strength(7days and 28days)	2 set /6-15 cum	12.6	4	4
8	WMM	Sieve Analysis	One Test		1	1
		Impact Value	One Test		1	1
		Flakiness Index	One Test		1	1
		Elongation Index	One Test		1	1

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

9	Paver Block	Compressive Strength	One Test		1	1
		Water Absorption	One Test		1	1
10	Chain Link Fencing	Average Thickness	One Test		1	1
		Dia of line wire	One Test		1	1
		Mesh size	One Test		1	1
		Nominal dia of mesh wire	One Test		1	1
		Bend Test	One Test		1	1
11	M.S Block Pipe	Yeild Stress	One Test		1	1
		Tensile Strength	One Test		1	1
		Elongation Percentage	One Test		1	1
12	M.S. Rectangular pole	Weight/Meter	One Test		1	1
		Yeild stress	One Test		1	1
		Tensile Strength	One Test		1	1
		Elongation Percentage	One Test		1	1
		Bend Test	One Test		1	1
13	Cement Concrete Designer Tiles	Water Absorption	One Test		1	1
		Wet Transverse Strength	One Test		1	1

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2021-01-06-18** **Date: 20-11-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-11-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 (Part 1,2 3,4,5, 6,11):1988 IS 4031 Part 1 DETERMINATION OF FINENESS BY DRY SIEVING, Clause 4.4 IS 4031 Part 2, Determination of Fineness by Blaine Air Permeability Method, Clause 5 IS 4031 Part 3, Determination of Soundness, Clause 5,Clause 6 IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 5, Determination of Initial & Final Setting Time, Clause 5 IS 4031 Part 11,DETERMINATION OF DENSITY , Clause 6
Date of test	:	18-11-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	Fineness by dry sieving (%)	1.85	_
2	Finess by Air permeablity method (m^2/kg,Min)	348.6	225m^2/kg, Min
3	Density (gm/cc)	3.15	_
4	Standard Consistency (%)	28.5%	Not specified
5	Initial Setting time	135 minutes	Not less than 30 minutes
6	Final Setting time	245 minutes	Not more than 600 minutes
7	Soundness (Le Chatelier's Method)	1.5mm	Not more than 10 mm

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.

All information furnished by Customer/Representative

Any correction in the report will make this report invalid

This report without prior written approval should not be reproduced or published in full or part.

Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

CIVIL PRO BANGALORE Date

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

****End of Report****

Format No: CP/TF/01

TEST REPORT OF PHYSICAL PROPERTIES OF CEMENT - 53 Grade

Lab ID	:	**CP-2021-01-06-18** **Date: 16-12-20**
Customer	:	Assistant Executive Engineer, Project Sub Division, BBMP, Bangalore.
Address	:	Project Sub Division, BBMP, Bangalore.
Project Name	:	"Improvements to Sahakaranagara Parks in Ward No.07 Byatrayanapura."
Agency	:	Sri. K Lakshmi Narayana Reddy, #688, 1st Floor, Vyalikaval Society, Near Chaitanaya Techno School, Veeranapalya, Bangalore-45.
Customer's Reference	:	EE(Project)/Ynk Zone/WO/118/2020-21
Source of Sample	:	Sample supplied by Agency
Sample Condition	:	Satisfactory
Date of Receipt	:	17-11-20
Sample Type	:	Birla Super 53grade
Reference to BIS codes	:	IS 12269 : 2013, 53 Grade Ordinary Portland cement Specification , IS 4031 Part 4, Determination of Consistency of Standard Cement Paste, Clause 5 IS 4031 Part 6, Determination of Compressive Strength, Clause 6
Date of test	:	18-11-20
Environmental Conditions during test	:	Temperature: 26°C Humidity: 72%

Compressive Strength

Sl.No.	Physical properties	Results	Requirement as per IS 12269: 2013
1	3 Days	28.5N/mm^2	Not less than 27 N/mm^2
2	7 Days	39.0N/mm^2	Not less than 37 N/mm^2
3	28 Days	58.5N/mm^2	Not less than 53 N/mm^2

* The results obtained are satisfactory as per standard requirements.

Note:

The results pertain to the samples received and tested.
All information furnished by Customer/Representative
Any correction in the report will make this report invalid
This report without prior written approval should not be reproduced or published in full or part.
Samples will be disposed after 30 days from the date of issue of test certificate

Asst. Executive Engineer
Project Division
Yelahanka Zone
BBMP, Bangalore - 92

FOR CIVIL Pro.

R RUDRAPRASAD
Authorized Signatory
Technical Manager

Page 1/1
****End of Report****